



# MATERIAL SAFETY DATA SHEET FOR STAINLESS STEEL SPRING WIRE TYPE 302/304

<b>Manufacturing Facility, Company or Subsidiary:</b>	Sumiden Wire Products Corporation
<b>Address:</b>	710 Marshall Stuart Drive Dickson, Tennessee 37055
<b>Phone (During normal business hours):</b>	615-446-3199
<b>Date of Preparation:</b>	May 25, 2005
<b>Product Name or Number:</b>	Stainless Steel Spring Wire Type 302/304
<b>Chemical Name:</b>	Stainless Steel

## Ingredients

<b>Base Metals:</b>				
	Fe:	(Balance)		
<b>Alloying Elements: (mass %)</b>				
	C:	0.08 Max.	Si:	1.00 Max.
	Mn:	2.00 Max.	P:	0.040 Max.
	S:	0.030 Max.	Ni:	8.00 – 10.00
	Cr:	18.00 - 19.00	N:	0.10 Max.
	Mo:	0.75 Max.	Cu:	0.75 Max.
<b>Surface Coating:</b>				
	Coating:	Ni & Sulfate (Na, K), Sulfate (Na, K)		
	Lubricant:	Stearate (Ca, Na)		

## Physical Data

Physical State: Solid  
 Appearance and Odor: Metal Grey, Odorless  
 Melting Point, Boiling Point:: N/A

## Personal Protection Information

Respiratory Protection: NIOSH/MSHA approved dust and fume respirator should be used if OSHA PEL is exceeded.  
 Hands, Arms, Body, Eyes, Use appropriate protective clothing, face shield when welding, burning or grinding.  
 Face Protection:

## Emergency Medical Procedures

First Aid: In case of excessive exposure to fumes or particulates, remove exposed person to fresh air, and if necessary administer oxygen and seek physician's assistance.

## Safety Information

Fire and Explosion: Steel products in the solid state present no fire or explosion hazard unless it is particulate or exposed in excessive oxygen.  
 Reactivity: Stable under normal condition.

## Spill Leak and Disposal Procedure

Spill and Leak: N/A to steel products in the solid state.  
 Disposal: N/A

### SUMIDEN WIRE PRODUCTS CORPORATION

Sales/Manufacturing: 710 Marshall Stuart Drive • Dickson, Tennessee 37055 • 615-446-3199 • 615-446-3197  
 Sales: San Clemente, California – 949-366-9577

Rev. 11/2005