



Sumiden Wire

**SPECIFICATIONS FOR STAINLESS ALLOY
TYPE 302**

ASTM A313 CHEMICAL REQUIREMENTS			
Chemical	Symbol	Minimum (%)	Maximum (%)
Carbon	C	--	0.12
Manganese	Mn	--	2.00
Phosphorus	P	--	0.045
Sulfur	S	--	0.030
Silicon	Si	--	1.00
Chromium	Cr	17.0	19.0
Nickel	Ni	8.0	10.0
Nitrogen	N	--	0.10